

## RANGE OF ETHYLENE – METHYL ACRYLATE GLYCIDYL METHACRYLATE (GMA)

Type	Grades	Acrylate	Acrylics ester content (%)	Melt Index (g/10 mn)	Glycidyl Methacrylate (%)	Melting Point (°C)	Vicat T°	Tensile strength at break (Mpa)	Elongation at break (%)	Flexural Modulus
Low Content	AX 8840	/	0	5	8	106	87	8	400	85
High Content	AX 8900	MA	24	6	8	65	<40	4	1100	<30
Test Method			FTIR	ASTM D 1238	FTIR	DSC	ASTM D 1525	ASTM D 638	ASTM D 638	ASTM D 790
ISO Standard			8985	ISO 1133	8985	11357-01	ISO 306	ISO R 527	ISO R 527	ISO 178