

# OREVAC<sup>®</sup> CA 100

## Maleic anhydride grafted Polypropylene

### Description

OREVAC<sup>®</sup> CA 100 is a chemically functionalized polypropylene with a high content of maleic anhydride. Grafting on polypropylene backbone is achieved with a processing technology which allows to optimize the compromise between chain breakdown and grafting efficiency.

Grafted maleic anhydride induces polarity to polypropylene and so outstanding adhesion properties on glass and natural fibers, and mineral fillers.

### Main application

OREVAC<sup>®</sup> CA 100 has been specially developed as coupling agent between PP and glass fiber, PP and mineral filler and PP and natural fibers.

### Main characteristics

Characteristics	Value	Unit	Test Method
Melt flow index (190°C – 0.325kg)	10	g/10min	ISO 1133 / ASTM D 1238
Melting point	167	°C	ARKEMA (DSC)
Vicat point	147	°C	ISO 306 (10 N)
Flexural Modulus	880	MPa	ISO 178
Strength at yield	22	MPa	ISO 527-2
Strength at break	22	MPa	ISO 527-2
Elongation at break	12	%	ISO 527-2

### Processing

OREVAC<sup>®</sup> CA 100 can be processed over a wide range of conditions. We suggest using standard Polyolefin working screw. Compounding can be achieved on conventional equipments such as monoscrews, twinscrews or kokneaders with usual temperatures.

### Storage

OREVAC<sup>®</sup> CA 100 is supplied in pellet in 25 kg bags and should be stored in dry conditions.

### Precautions of use

A safety data sheet as well as information on handling and storage of the OREVAC<sup>®</sup> CA 100 is available close to your correspondent ARKEMA or on the site [www.arkemagroup.com](http://www.arkemagroup.com) under heading FDS.

February 2006

The information contained in this document is based on trials carried out by our Research Centers and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



Technical Polymers Division  
4/8, cours Michelet – La Défense 10  
92800 Puteaux - France

[www.arkemagroup.com](http://www.arkemagroup.com)