

# LOTADER<sup>®</sup> 3210

LOTADER<sup>®</sup> 3210 is a random ethylene-butyl acrylate-maleic anhydride terpolymer.

LOTADER<sup>®</sup> 3210 is a versatile adhesive for extrusion coating or lamination, designed as:

- Concentrate to be used in dry blend with LDPE. LOTADER<sup>®</sup> 3210 improves adhesion of LDPE on aluminum foils, metallized or primerized films.
- Ready for use resin to be used pure. LOTADER<sup>®</sup> 3210 gives excellent adhesion on substrates like aluminum foil, metallized plastics, paper, board, PE and some plastic films like BOPP.
- Coextrusion tie layer for PE/PA in extrusion coating process.

LOTADER<sup>®</sup> 3210 can also be used as a coupling agent for mineral filled compounds such as halogen free flame retardant wires and cables, a compatibiliser for polyamide/polyolefin blends and a modifier for polyamides.

## Typical Properties

	Test Method	Unit	Typical Value
Methyl Acrylate Content	FTIR (internal method)	%.-wt.	6
Maleic Anhydride Content	FTIR (internal method)	%.-wt.	3.1
Melt Index (190°C/2.16kg)	ISO 1133 / ASTM D1238	g/10min.	5
Melting Point	ISO 11357-3	°C	107
Vicat Softening Temperature (10N) <sup>1</sup>	ISO 306 / ASTM D1525	°C	76
Density	ISO 1183 / ASTM D1505	g/cm <sup>3</sup>	0.94
Flexural Modulus <sup>1</sup>	ISO 178 / ASTM D790	MPa	120
Elongation at break <sup>1</sup>	ISO 527-2 / ASTM D638	%	600
Tensile strength at break <sup>1</sup>	ISO 527-2 / ASTM D638	MPa	12
Hardness Shore D <sup>1</sup>	ISO 868 / ASTM D2240	-	46

<sup>1</sup>: On compression molded samples.

*The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Corporation's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Functional Polymer invoices and/or order acknowledgments. Except as expressly provided in SK Corporation's standard terms and conditions of sale, SK Corporation makes no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Corporation assumes no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. SK Functional Polymer is a subsidiary of SK Global Chemical.*

## Processing

LOTADER® 3430 can be extruded with standard polyolefin extrusion equipment with typical melt temperature of 270°C and up to 320°C-330°C.

LDPE purge is recommended before extruder shutdown.

## Storage, Handling & Safety

LOTADER® 3210 is usually packed in waterproof bags or rigid containers with waterproof liner. It should be stored in dry conditions and be kept out of moisture in an aerated building.

Improper storage conditions may cause degradation and could have consequences on physical properties of the product. It is recommended to reseal the bag or the liner after use to protect LOTADER® 3210 against moisture.

Safety data sheet as well as information on handling and storage of the LOTADER® 3210 is available upon request to your SK Functional Polymer representative.

## Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

*The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Corporation's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Functional Polymer invoices and/or order acknowledgments. Except as expressly provided in SK Corporation's standard terms and conditions of sale, SK Corporation makes no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Corporation assumes no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. SK Functional Polymer is a subsidiary of SK Global Chemical.*