

# LOTADER<sup>®</sup> 6200

LOTADER<sup>®</sup> 6200 is a random ethylene-ethyl acrylate-maleic anhydride terpolymer.

Due to its properties, reactivity, fluidity and compatibility with tackifying resins and waxes, LOTADER<sup>®</sup> 6200 is suitable as additive for hot melt adhesive formulations and as coupling agent in mineral filled compounds.

## Typical Properties

	Test Method	Unit	Typical Value
Ethyl Acrylate Content	FTIR (internal method)	%.-wt.	6.5
Maleic Anhydride Content	FTIR (internal method)	%.-wt.	2.8
Melt Index (190°C/2.16kg)	ISO 1133 / ASTM D1238	g/10min.	40
Melting Point	ISO 11357-3	°C	102
Vicat Softening Temperature (10N) <sup>1</sup>	ISO 306 / ASTM D1525	°C	66
Density	ISO 1183 / ASTM D1505	g/cm <sup>3</sup>	0.94
Flexural Modulus <sup>1</sup>	ISO 178 / ASTM D790	MPa	95
Elongation at break <sup>1</sup>	ISO 527-2 / ASTM D638	%	600
Tensile strength at break <sup>1</sup>	ISO 527-2 / ASTM D638	MPa	6
Hardness Shore D <sup>1</sup>	ISO 868 / ASTM D2240	-	36
Ring & Ball Temperature	ASTM E28	°C	119

<sup>1</sup>: On compression molded samples.

*The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Corporation's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Functional Polymer invoices and/or order acknowledgments. Except as expressly provided in SK Corporation's standard terms and conditions of sale, SK Corporation makes no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Corporation assumes no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. SK Functional Polymer is a subsidiary of SK Global Chemical.*

## Processing

Heat stability of acrylate comonomer allows processing temperatures as high as for polyamides, which is the main material using LOTADER® 6200 as impact modifier. However, to minimize the generation of gels, it is recommended to purge the equipment with LDPE after a run is completed.

LOTADER® 6200 is not corrosive.

## Storage, Handling & Safety

LOTADER® 6200 is usually packed in waterproof bags or rigid containers with waterproof liner. It should be stored in dry conditions and be kept out of moisture in an aerated building. Improper storage conditions may cause degradation and could have consequences on physical properties of the product. It is recommended to reseal the bag or the liner after use to protect LOTADER® 6200 against moisture.

Safety data sheet as well as information on handling and storage of the LOTADER® 6200 is available upon request to your SK Functional Polymer representative.

## Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

*The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Corporation's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Functional Polymer invoices and/or order acknowledgments. Except as expressly provided in SK Corporation's standard terms and conditions of sale, SK Corporation makes no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Corporation assumes no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. SK Functional Polymer is a subsidiary of SK Global Chemical.*